



FIX8 TRANSLUCENT

Revision: 011/2011

Page 1 of 2

Technical Data:

Base	Silicone Structural – Anti Mould
Consistency	Paste
Curing System	Moisture Cure
Skin Formation	12 minutes (23 ⁰ C & 50%R.H)
Tack Free Time	3 hours (23 ⁰ C & 50%R.H)
Curing Rate	3mm/24 Hrs
Density	1.34 g/cm ³
Shrink	None
Elongation	300%
Hardness (Shore A)	40±5
Tensile Strenght	>0.8 Mpa (ISO8339)
Shear Strength	> 1.0 Mpa
Movement Capability	25%

(*) Values may vary depending on environmental conditions

Product:

Fix8 Translucent is a high quality architectural grade single component high modulus structural silicone sealant, neutral cure, that exhibits excellent physical properties. Suitable for typical sealing and structural bonding in glazing applications with metal, aluminium, Corian® most plastics and fibreglass substrates. Fix8 Translucent displays excellent weatherability and UV resistance curing to a high performance flexible rubber sealant in weatherproofing and structural applications. Fix8 Translucent is suitable for glass curtain wall construction.

Characteristics:

- Primelrless adhesion on most substrates (except Teflon, PE and PP)
- Excellent UV resistance
- Very good filling capacities
- Neutral cure
- Excellent stability
- Superior weather resistance up to 20 years
- Good compatability with other sealants
- Permanently elastic
- Colour Fast
- Suitable for marine exposure

Applications:

Installation of glass windows
 Sealing of all openings in roof constructions
 Sealing and bonding within the Automotive industry
 Mounting and sealing of window frames
 Bonding and sealing of coachwork within the transportation industry

Packaging:

Colour – Translucent
 Packaging – 300mL Cartridge

Shelf life:

12 months from date of production; In unopened packaging stored in a cool and dry place at temperatures between +5°C and +27°.

Surfaces:

State of Surface: clean, dry, free of dust and grease
Priming: For porous substrates Primer PR10 may be applied. Polypropylene; Primer PR20. Non-porous substrates may be cleaned with Methylated Spirits or alcohol cleaner
 We Recommend Compatibility Tests

Note: The contents contained in this documentation are the result of our experiments and our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the real world of possible applications which are out of our control we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments and compatibility tests.



FIX8 TRANSLUCENT

Revision: 011/2011

Page 2 of 2

Application:

Method: Manual or pneumatic caulking gun
Application temperature: +4°C to +40°C
Tooling: Mild diluted soapy solution before skin formation

Joint Dimensions:

Minimal Width: 5mm
Maximum Width: 30mm
Minimum Depth: 5mm
Recommendation: width of joint = 2 x depth

Health- and Safety Recommendation:

Apply the usual industrial hygiene. Wear gloves . Safety Glasses. Volatile compound released during curing, ensure adequate ventilation

Remarks:

- Fix8 Translucent can not be overpainted
- Fix8 Translucent is chemically neutral (pH=7)
- Fix8 Translucent can be applied to a wide variety of substrates. Due to the fact that the specific properties of substrates will differ from manufacturer to manufacturer we strongly recommend compatibility tests.
- Not suitable for mirrors

Note: The contents contained in this documentation are the result of our experiments and our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the real number of possible applications which are out of our control we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments and compatibility tests.

Fixtech Pty Ltd. PO Box 568, Southport, Qld 4215. Tel: +61 (0)7 5530 1099. Fax: +61 (0)7 5530 1322

Email: info@fixtech.com.au

Web: www.fixtech.com.au